

## EFFECTIVENESS OF DIETHANOLAMINE (DEA) ADDITION ON BAND GAP VALUE OF SnO<sub>2</sub> BY USING SOL-GEL METHODS

Miftah Patriela & Hary Sanjaya

Universitas Negeri Padang

miftahpatriela1@gmail.com; hary.s@fmipa.unp.ac.id

### Article Info:

Submitted:	Revised:	Accepted:	Published:
Feb 9, 2024	Feb 15, 2024	Feb 18, 2024	Feb 21, 2024

### Abstract

The need for electrical energy is increasing with the increase in the economy and population in Indonesia. Fossil energy sources are used as fuel to produce electrical energy and will run out if used continuously. Fossil energy sources can be replaced by using New Renewable Energy (NRE) to meet national electrical energy needs. The purpose of adding additives in this study is to observe the effectiveness of the addition of DEA on the band gap value, crystal phase, and surface morphology on SnO<sub>2</sub>. In this study using the sol-gel method for the synthesis of SnO<sub>2</sub>. The sol-gel method is the conversion of monomers into colloidal solutions (sol) which serve as precursors for integrated networks (gels) either discrete particles or network polymers. SnO<sub>2</sub> nanomaterials will be characterized by UV-DRS Spectrophotometer. The results of characterization of SnO<sub>2</sub> nanomaterials with the addition of Diethanolamine additives as much as 1.5 mL have obtained a band gap value of 3.60 eV.

**Keywords** : Diethanolamine ; SnO<sub>2</sub> Nanomaterial ; Sol-gel

## INTRODUCTION

The need for electrical energy is increasing with the increasing economy and population in Indonesia (Adistia et al., 2020). Information that has been obtained from Databoks.id in 2023 shows that Indonesia consumed electricity per capita of 1,089 kWh per capita in 2020 and an increase in 2021 of 1,123 kWh per capita. Electricity consumption in Indonesia was recorded in 2022 to have reached 1,173 kWh per capita. Fossil energy sources are used as fuel to produce electrical energy and will run out if used continuously (Ryanuargo et al., 2013). Fossil energy sources can be replaced by using New Renewable Energy (EBT) to meet national electrical energy needs (Adistia et al., 2020). One of the New Renewable Energy (EBT) that can be developed is semiconductors. One of the uses of semiconductors in Indonesia is the production of electronic devices that use Lithium ions as semiconductor materials (Brunner, 2021). Lithium ion batteries are sensitive to high temperatures and can burn when exposed to extreme heat and the production of lithium ion batteries is expensive, making it less accessible to consumers (Shobana, 2019). The use of Lithium ion batteries can be replaced by using other semiconductor alternatives.

Semiconductors are materials that can conduct electricity within a certain range. The electrical and optical properties of semiconductors have a major impact on the performance of solar cells, photo electrocatalysts and photo catalysts (Wang et al., 2021). Semiconductors have several advantages, namely that they can be processed by low-temperature deposition, have a smooth / grainy coating, manufacture large areas on glass and lack of long-range regularity making plastic substrates flexible (Kim et al., 2018). Semiconductor applications include solar cells, batteries, and transparent electrodes as well as gas sensors and catalysts (Patel et al., 2021). Some semiconductor materials that can be applied such as  $\text{TiO}_2$ ,  $\text{ZnO}$ ,  $\text{CoO}$ ,  $\text{CdO}$ ,  $\text{LiCoO}_2$ , and  $\text{SnO}_2$  (Shobana, 2019).

Tin dioxide ( $\text{SnO}_2$ ) is an n-type oxide semiconductor with a band gap of 3.6 eV that has good electrical conductivity (Kose et al., 2015). Basically tin oxide exists in the form of  $\text{SnO}$ ,  $\text{SnO}_2$ ,  $\text{Sn}_3\text{O}_4$ , and  $\text{Sn}_2\text{O}_3$ . Tin oxide in the form of  $\text{SnO}$  is less stable so that through oxidation it is converted to  $\text{SnO}_2$ . The advantages of  $\text{SnO}_2$  are good transparent conductor stability because it has high electrical conductivity and is transparent to visible light. In addition,  $\text{SnO}_2$  does not experience corrosion and the tin element is easily available so that production is cheaper. The wide optical band gap of  $\text{SnO}_2$  and transparency to visible

wavelengths make SnO<sub>2</sub> suitable for several applications such as solar cells, gas sensors, catalysts, batteries, transistors, and transparent electrodes (Patel et al., 2021).

Several methods in the synthesis of SnO<sub>2</sub> materials, such as magnetron sputtering method (Ning et al., 2009), chemical coprecipitation method (Liu et al., 2012), function theory (Isherwood et al., 2015), hydrothermal method (Borhade et al., 2019) and sol-gel method (Kim et al., 2018). The sol-gel process is the conversion of monomers into colloidal solutions (sols) that serve as precursors for integrated networks (gels) of either discrete particles or network polymers (Ansari et al., 2018). The sol-gel method has advantages, namely good product homogeneity, easy to control the composition, uses relatively low temperatures, large coating areas, low equipment costs, has good optical properties (Ilican et al., 2008), simple, and low energy and material consumption levels (Saini et al., 2007).

Arini, et al, have conducted research on SnO<sub>2</sub> synthesis without using additives to produce SnO<sub>2</sub> morphology that looks smooth with a particle size of 71.5 nm (Arini et al., 2021). Research by Aziz, et al, using polyethylene glycol additives in the synthesis of SnO<sub>2</sub> produced a smoother morphology with a smaller particle size of about 22-31 nm (Aziz et al., 2012). The use of additives can affect the morphology of SnO<sub>2</sub> material so that the optimum material is obtained. Additives can produce a homogeneous material (Ningsih, 2016), stabilizers (Suchanek et al., 2018), and can increase thermal stability and oxidation resistance in semiconductors (Widodo, 2020). The synthesis of oxide compound nanoparticles requires the use of additives as capping agents to improve the properties and semiconductor applications of these nanoparticles (Fathia, 2018). One of the additives that can be used as a capping agent is Diethanolamine (DEA).

Diethanolamine (DEA) is an organic compound with the formula C<sub>4</sub>H<sub>11</sub>NO<sub>2</sub>. DEA can act as both base and acid (amphoteric). In semiconductor synthesis, the use of DEA has advantages such as increasing electrical conductivity, resistance to oxidation and optical properties in semiconductors (Rahayu et al, 2020) so that the use of DEA as an additive is needed in the synthesis of SnO<sub>2</sub> using the sol-gel method to produce materials with high homogeneity (Kasuma et al., 2020).

## METHODS

The tools used were beakers, measuring cups, vaporizer cups, watch glass, measuring pipettes, desiccators, mortar and pestle, magnetic stirrer, stirrer bar, furnace, and UV-Diffuse Reflectance (UV-DRS) spectrophotometer (Thermoscientific Genesys 30).

$\text{SnCl}_2 \cdot 2\text{H}_2\text{O}$  was dissolved with 50 ml of methanol solvent with varying concentrations of 0.8 mmol, 1 mmol and 1.2 mmol, covered with plastic wrap, and homogenized with a magnetic stirrer for 40 minutes. Added 1.5 ml, 2 ml, and 2.5 ml of DEA to each solution, stirring for  $\pm 1$  hour. Then sonication was carried out on the solution for 30 minutes at 45 W so that a homogeneous solution (sol) was obtained and allowed to stand for 1 x 24 hours to stabilize the sol. Next, the sample was dried in an oven at  $110^\circ\text{C}$  for  $\pm 1$  hour. The gel obtained was calcined with a furnace at a temperature of  $350^\circ\text{C}$  for  $\pm 3$  hours to obtain  $\text{SnO}_2$ . The sample is stored in a desiccator, after cooling the sample is crushed using a mortar and pestle so that the sample can be characterized (Kasuma et al., 2020). UV-DRS functions to determine optical properties (Mugundan et al., 2015) at wavelengths of 200-800 nm (Borhade et al., 2019). The band gap energy and wavelength can be identified from the UV-DRS spectrum (Mugundan et al., 2015).

## RESULTS AND DISCUSSION

### 1. Effect of Precursor Concentration Variation

UV-DRS spectrophotometer is used to determine the band gap value resulting from the synthesis of  $\text{SnO}_2$ . In this study, UV-DRS Spectrophotometer measurements were taken at a wavelength of 185-1100 nm. In the synthesis of  $\text{SnO}_2$ , several variations in the concentration of  $\text{SnCl}_2 \cdot 2\text{H}_2\text{O}$  precursors were carried out to determine the optimum band gap value of  $\text{SnO}_2$  that had been synthesized. In this study using variations in precursor concentrations of 0.8 mmol, 1 mmol, and 1.2 mmol. The band gap value on  $\text{SnO}_2$  is calculated using the Kubelka-munk equation (Sanjaya et al., 2018). The following are the results of band gap measurements with variations in precursor concentration can be seen in table 1.

Table 1. Band gap Energy with Effect of Precursor Concentration

Precursor Concentration	Band gap Value (Eg)
0.8 mmol Without DEA	6.29 eV
0.8 mmol + 1.5 mL DEA	3.70 eV
1 mmol + 1.5 mL DEA	3.60 eV
1.2 mmol + 1.5 mL DEA	4.17 eV

Based on table 1, it can be seen that the band gap value at a concentration of 0.8 mmol without the addition of DEA additives has a band gap value of 6.29 eV which indicates that SnO<sub>2</sub> nanomaterials are insulators. This is in accordance with the reference which states that the insulator has a large band gap value of > 4 eV (Costa et al., 2016). SnO<sub>2</sub> nanomaterial with a concentration of 0.8 mmol with the addition of 1.5 mL DEA obtained a band gap value of 3.70 eV. This shows that the addition of DEA additives can reduce the band gap value of SnO<sub>2</sub> nanomaterials. At a concentration of 1 mmol there is a decrease in band gap value of 3.60 eV then an increase in band gap value at a concentration of 1.2 mmol of 4.17 eV.

The difference in band gap value is due to a decrease in crystallite size resulting in an increase in band gap value towards the conductor (Rahmawati & Nazriati, 2022). According to Ningsih, et al, in 2021 stated that the bandgap value increases between the valence band and the conduction band with a decrease in particle size so that the reaction occurs faster in the visible light region (Ningsih et al., 2021). According to Ningsih et al, the decrease in band gap value is caused by the interaction between the electron band and the delocalization of electrons in transition ions so that metal ion substitution is formed (Ningsih et al., 2021). In addition, the reduced band gap value causes the distance between the valence band and the conduction band to get closer and electron excitation becomes faster so that less photon energy is needed for electron excitation from the valence band to the conduction band (Ningsih et al., 2019). This shows that the greater the band gap value to the insulator, the greater the photon energy required for electron excitation from the valence band to the conduction band. Based on table 1, the optimum band gap value has been obtained at a concentration of 1 mmol with a value of 3.60 eV because the band gap value obtained is smaller than other concentrations. This shows the distance between the valence band and the conduction band is closer and the particle size is smaller with a larger surface area and higher reactivity. The band gap value of SnO<sub>2</sub> with a precursor

concentration of 1 mmol is in accordance with the reference which states that the band gap value of SnO<sub>2</sub> nanoparticles is 3.60 eV (Al-saadi et al., 2019).

## 2. Effect of Addition of Diethanolamine (DEA) Additive

In the synthesis of SnO<sub>2</sub>, variations in the addition of diethanolamine (DEA) additives were carried out to obtain the optimum band gap value in SnO<sub>2</sub> synthesis. In this study, variations in the volume addition of DEA additives were carried out with variations of 1.5 mL, 2 mL, and 2.5 mL. UV-DRS Spectrophotometer measurements were taken at a wavelength of 185-1100 nm. The following are the results of band gap measurements using a UV-DRS Spectrophotometer on variations in the volume of DEA additives in table 2.

Table 2. Band gap Energy with Effect of DEA

Volume of DEA (mL)	Band gap Value (Eg)
1.5	3.60 eV
2	3.62 eV
2.5	3.79 eV

Table 2 shows that the band gap value with variation of DEA additive volume has been obtained with values ranging from 3.60 eV - 3.79 eV. The smallest band gap value is at the addition of 1.5 mL DEA volume with a band gap value of 3.60 eV while the largest value is at the addition of 2.5 ml DEA volume with a band gap value of 3.79 eV. This shows that the band gap value is directly proportional to the addition of DEA volume in SnO<sub>2</sub> synthesis. The greater the addition of DEA volume, the greater the band gap value obtained in SnO<sub>2</sub> synthesis. The increasing band gap value is due to the non-uniform microstrain resulting from the relaxation of the grain surface and unsaturated bonds on the surface of the nanoparticles which can change the energy level thus affecting the band gap value (Wang et al., 2017). The optimum band gap value is obtained at the addition of 1.5 mL DEA volume because it has the smallest band gap value of 3.60 eV which is in accordance with the reference which states that SnO<sub>2</sub> has a band gap of 3.60 eV (Al-saadi et al., 2019). This small bandgap value has a small particle size and large surface area so that its reactivity increases in visible light (Ningsih et al., 2021).

## CONCLUSION

The effect of the addition of DEA additives on the synthesis of SnO<sub>2</sub> is the more the addition of DEA volume, the higher the band gap value of SnO<sub>2</sub> nanomaterials. The effect of SnCl<sub>2</sub>.2H<sub>2</sub>O precursor concentration on SnO<sub>2</sub> synthesis is at a concentration of 0.8 mmol to 1 mmol there is a decrease in band gap value and then an increase in band gap value at a concentration of 1.2 mmol. The difference in band gap value occurs due to differences in particle size which can affect the band gap value of SnO<sub>2</sub>.

## REFERENCES

- Adistia, N. A., Nurdiansyah, R. A., Fariko, J., Vincent, V., & Simatupang, J. W. (2020). Potensi energi panas bumi, angin, dan biomassa menjadi energi listrik di Indonesia. *TESLA: Jurnal Teknik Elektro*, 22(2), 105-116.
- Al-Saadi, T. M., Hussein, B. H., Hasan, A. B., & Shehab, A. A. (2019). Study the structural and optical properties of Cr doped SnO<sub>2</sub> nanoparticles synthesized by sol-gel method. *Energy Procedia*, 157, 457–465. <https://doi.org/10.1016/j.egypro.2018.11.210>
- Ansari, F., Sobhani, A., & Salavati-Niasari, M. (2018). Simple sol-gel synthesis and characterization of new CoTiO<sub>3</sub>/CoFe<sub>2</sub>O<sub>4</sub> nanocomposite by using liquid glucose, maltose and starch as fuel, capping and reducing agents. *Journal of Colloid and Interface Science*, 514, 723–732.
- Arini, T., Lalasari, L. H., Setiawan, I., Andriyah, L., Natasha, N. C., Yunita, F. E., & Suharyanto, A. (2022). STRUKTUR KRISTAL DAN MORFOLOGI PERMUKAAN – SINTESIS SNO<sub>2</sub> MENGGUNAKAN METODE SOL-GEL. *Jurnal Rekayasa Mesin*, 13(2), 427–433. <https://doi.org/10.21776/jrm.v13i2.1048>
- Aziz, M., Abbas, S. S., Baharom, W. R. W., & Mahmud, W. Z. W. (2012). Structure of SnO<sub>2</sub> nanoparticles by sol-gel method. *Materials Letters*, 74, 62–64. [doi:10.1016/j.matlet.2012.01.073](https://doi.org/10.1016/j.matlet.2012.01.073)
- Borhade, V., Tope, D. R., & Sangle, S. L. (2019). Synthesis, characterization and photocatalytic application of CuSnO<sub>3</sub> perovskite oxide. *Journal of Emerging Technologies and Innovative Research*, 6(3), 382–386.
- Brunner, I. M. I. M., & Brunner, S. M. (2021). Pemilihan Baterai Kendaraan Listrik dengan Metoda Weighted Objective. *Jurnal Serambi Engineering*, 6(1).
- Costa, J. C. S., Taveira, R. J. S., Lima, C. F. R. A. C., Mendes, A., & Santos, L. M. N. B. F. (2016). Optical band gaps of organic semiconductor materials. *Optical Materials*, 58, 51–60. <https://doi.org/10.1016/j.optmat.2016.03.041>
- Fathia, A. (2018). Sintesis dan karakterisasi graphene oxide terkombinasi nanopartikel perak dalam fase cair. Yogyakarta: Universitas Negeri Yogyakarta.
- Ilican, S., Caglar, Y., Caglar, M., & Yakuphanoglu, F. (2008). Structural, optical and electrical properties of F-doped ZnO nanorod semiconductor thin films deposited by sol-gel process. *Applied Surface Science*, 255(5), 2353–2359.

- Isherwood, P. J. M., Butler, K. T., Walsh, A., & Walls, J. M. (2015). A tunable amorphous p-type ternary oxide system: The highly mismatched alloy of copper tin oxide. *Journal of Applied Physics*, *118*(10), 105702.
- Kasuma, S., Ningsih, W., Nasra, E., Rahayu, Y., Kimia, J., Matematika, F., Alam, P., & Padang, U. N. (2020). Sintesis dan karakterisasi nanopartikel  $\text{Co}^{2+}$  doped ZnO dengan menggunakan metode sol-gel. *Indonesian Journal of Chemical Science*, *9*(1), 24–30.
- Kim, B. N., Seo, G. K., Hwang, S. W., Yu, H., Ahn, B., Seo, H., & Cho, I. S. (2018). Photophysical properties and photoelectrochemical performances of sol-gel derived copper stannate ( $\text{CuSnO}_3$ ) amorphous semiconductor for solar water splitting application. *Ceramics International*, *44*(2), 1843–1849.
- Kose, H., Karaal, S., Aydin, A. O., & Akbulut, H. (2015). Structural properties of size-controlled  $\text{SnO}_2$  nanopowders produced by sol-gel method. *Materials Science in Semiconductor Processing*, *38*, 404–412. <https://doi.org/10.1016/j.mssp.2015.03.028>
- Liu, T., Du, R. bin, & Kong, X. jun. (2012). Preparation and electrochemical properties of amorphous tin-copper composite oxide  $\text{CuSnO}_3$ . *Advanced Materials Research*, *535–537*, 31–35.
- Mugundan, S., Rajamannan, B., Viruthagiri, G., Shanmugam, N., Gobi, R., & Praveen, P. (2015). Synthesis and characterization of undoped and cobalt-doped  $\text{TiO}_2$  nanoparticles via sol-gel technique. *Applied Nanoscience (Switzerland)*, *5*(4), 449–456.
- Ning, T., Ji, F., Ma, J., Song, Z., Pei, X., & Tan, Y. (2009). Study on fabrication and properties of copper-tin-oxide thin films. *Advanced Materials Research*, *79–82*, 787–790.
- Ningsih, S. K. W., Nizar, U. K., Bahrizal, Nasra, E., & Suci, R. F. (2019). Effect of egg white as additive for synthesis and characterization of Al doped ZNO nanoparticles by using sol-gel method. *Journal of Physics: Conference Series* *1185*. doi:10.1088/1742-6596/1185/1/012029.
- Ningsih, S. K. W., Sanjaya, H., Bahrizal, Nasra, E., & Yurnas, S. (2021). Synthesis of  $\text{Cu}^{2+}$  Doped ZnO by the Combination of Sol-Gel-Sonochemical Methods with Duck Egg Albumen as Additive for Photocatalytic Degradation of Methyl Orange. *Indonesian Journal of Chemical Science*, *21*(3), 564–574.
- Ningsih, S. K. W. (2016). *Sintesis Anorganik*. Padang: UNP Press.
- Patel, G. H., Chaki, S. H., Kannaujiya, R. M., Parekh, Z. R., Hirpara, A. B., Khimani, A. J., & Deshpande, M. P. (2021). Sol-gel synthesis and thermal characterization of  $\text{SnO}_2$  nanoparticles. *Physica B: Condensed Matter*, *613*. <https://doi.org/10.1016/j.physb.2021.412987>
- Saini, K. K., Sharma, S. D., Chanderkant, Kar, M., Singh, D., & Sharma, C. P. (2007). Structural and optical properties of  $\text{TiO}_2$  thin films derived by sol-gel dip coating process. *Journal of Non-Crystalline Solids*, *353*(24–25), 2469–2473.
- Sanjaya, H., Hardeli, & Syafitri, R. (2018). Degradasi Metil Violet Menggunakan Katalis  $\text{ZnO-TiO}_2$  secara Fotosonolisis. *EKSAKTA: Berkala Ilmiah Bidang MIPA*, *19*(1), 91–99.
- Shobana, M. K. (2019). Metal oxide coated cathode materials for Li ion batteries e A review. *Journal of Alloys and Compounds*, *477–487*. <https://doi.org/10.1016/j.jallcom.2019.06.194>.
- Suchanek, K., Bartkowiak, A., Perzanowski, M., & Marszalek, M. (2018). From monetite



- plate to hydroxyapatite nanofibers by monoethanolamine assisted hydrothermal approach. *Scientific Reports*, 8(1), 15408.
- Rahayu, S., Herawati, N., & Wijaya, M. (2020). Sintesis Nanopartikel Mangan Oksida dengan Metode Sol Gel dan Uji Aktivitas Katalitik terhadap Degradasi Zat Warna Rhodamin B. *Jurnal Chemica*, Vol.21(2), 190-199.
- Rahmawati, E. R., & Nazriati, N. (2022). Biosintesis dan karakterisasi nanopartikel tembaga oksida (CuO) menggunakan ekstrak rimpangg kencur (*Kaempferia galanga* L.). *Jurnal Teknik Kimia*, 28 (3), 141-151. <https://doi.org/10.36706/jtk.v28i3.1232>.
- Ryanuargo, Anwar, S., & Sari, S. P. (2013). Generator mini dengan prinsip termoelektrik dari uap panas kondensor pada sistem pendingin. *Jurnal Rekayasa Elektrika*, 10(4), 180–185.
- Wang, B., Biesold, G. M., Zhang, M., & Lin, Z. (2021). Amorphous inorganic semiconductors for the development of solar cell, photoelectrocatalytic and photocatalytic applications. *Chemical Society Reviews*, 50(12), 6914–6949.
- Wang, M., Wang, T., Song, S. H., Ravi, M., Liu, R. C., & Ji, S. S. (2017). Effect of calcination temperature on structural, magnetic and optical properties of multiferroic YFeO<sub>3</sub> nanopowders synthesized by a low temperature solidstates reaction. *Ceramics International*, 43(13), 10270-10276. <https://doi.org/10.1016/j.ceramint.2017.05.056>
- Widodo, S. (2020). Review Sensor Gas Berbasis Metal Oksida Semikonduktor Untuk Mendeteksi Gas Polutan Yang Selektif Dan Sensitif. *Techno-Socio Ekonomika*, 12(2), 92-112.